



Despriet Gebroeders NV
Looplife Polymers Site
Nijverheidsstraat 2 (B5)
B-2235 Huslhout, Belgium
info@looplife-polymers.eu
www.looplife-polymers.eu

TECHNICAL DATA SHEET

LOOPLIFE r-HDPE

Polyolefins

R-HDPE01C-BK / GRADE

REPROCESSED HIGH DENSITY POLYETHYLENE / PRODUCT NAME

Description

r-HDPE grades from LOOPLIFE POLYMERS are reprocessed from homogeneous and clean/washed sources of high density polyethylene (HDPE). Product is supplied in the form of pellets.

PHYSICO-CHEMICAL PROPERTIES

Chemical name	High Density Polyethylene			Residual moisture	ppm	Max	1000
Granulometry	pellets/g	25	-	70	Ash content @450°C	%	4,1
Density	g/cm ³	0,958			Melt index @230°C, 2,16kg	g/10 min	-
Melt index @190°C, 2,16kg	g/10 min	-			Melt index @230°C, 5kg	g/10 min	-
Melt index @190°C, 5kg	g/10 min	2,5	-	3,5			

MECHANICAL PROPERTIES

Stress at yield	MPa		Tensile modulus	MPa	648
Stress at break	MPa	3,2	IZOD	kJ/m ²	28,9
Flex modulus	MPa	718	Strain at Yield	%	15,4
Tensile strength	MPa	18,4	Strain at Break	%	64

SENSORY CHARACTERISTICS

Clarity	Opaque
Shape	Lenticular to cylindrical
Color	Black

PURITY

Other fraction	May content up to 10% PP
----------------	--------------------------

REGISTRATION

CAS nummer	9002-88-4
------------	-----------

PACKAGING

Standard: Big bag (1200kg Net Weight)

PROCESSING INFORMATION

TRANSPORT STORAGE CONDITIONS

Keep in a dry, well ventilated place. Do not store with oxidizing and self-igniting products
Big bags on pallet

SHELF-LIFE

Shelf-life	36 months
------------	-----------